

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : Enviro-Foam
Unit 1
25 South Pine Road
Brendale QLD 4500

Test Number : 16-000395
Issue Date : 17/02/2016
Print Date : 26/02/2016

Replacement of Initial Report dated :17/02/2016

Sample Description Woven coated fabric
Colour : Grey

ASTM E96-2012

Water Vapour Transmission - Water Method

| | |
|------------------|-----------------------------|
| Dish Diameter | 86.0 mm |
| Temperature Mean | 23.0 °C |
| Humidity Mean | 50.8 % |
| Specimen | |
| 1 | 654.7 g/24h.m ² |
| 2 | 629.0 g/24h.m ² |
| 3 | 418.8 g/24h.m ² |
| Mean | 567.52 g/24h.m ² |

86mm diameter petri dish used.

Hot melt glue sealant used.

Sample tested with uncoated face towards water.

Glue would not stick to coated face to form a sealed bond so specimens were tested with the uncoated face towards the water.

49661

9945

Page 1 of 1

© Australian Wool testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025

- Chemical Testing
- Mechanical Testing
- Performance & Approvals Testing

: Accreditation No.

983

: Accreditation No.

985

: Accreditation No.

1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by



APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc. (Hons)
MANAGING DIRECTOR